

# Neotex<sup>®</sup> Metal Primer

## Water-based, one-component anti-corrosive primer

### Description

Water-based, one-component anti-corrosive primer for old or new metallic surfaces

### Fields of application

On old or new surfaces of iron or steel, in interior or exterior areas, which are to be covered with water-based waterproofing coatings (e.g. **Neoproof<sup>®</sup> PU W**, **Neorooft<sup>®</sup>**, **Revinex<sup>®</sup> Elastic**, etc.)

### Properties - Advantages

- Ideal for the anti-corrosive protection of metallic surfaces, prior to the application of water-based coatings
- Very strong adhesion on metallic substrates
- Resilient to adverse weather conditions and industrial atmosphere
- Suitable for interior and exterior applications, even in seaside areas



### Colour

Terracotta

### Packing

3L and 1L

### Technical characteristics

Density (EN ISO 2811-1)	1,29kg/L (±0,05)
-------------------------	------------------

**Consumption: 80-100ml/m<sup>2</sup> in one layer**

### Application conditions

Substrate moisture content	<4%
Relative air humidity (RH)	<65%
Application temperature (ambient - substrate)	+12°C min. / +35°C max.

### Curing details

Drying time (+25°C)	2-3 hours
Dry to recoat - overcoat (+25°C)	4-6 hours

*\* Low temperatures and high humidity during application and/or curing prolong the above times, while high temperatures reduce them*

## Instructions for use

### **Substrate preparation**

The metallic surfaces must be properly prepared by sandblasting or sanding with a wire brush and should be dry, free of dust, dirt, greasy and oily substances, as well as any poorly adhering coatings. In rusty areas, it is recommended to locally apply the chemical rust converter **Neodur® Metalforce**. New metallic surfaces should be degreased with solvent **Neotex® 1021**.

### **Application**

After thorough stirring, **Neotex® Metal Primer** is applied, diluted with water up to 5%, in one layer by roller or brush. For enhanced anti-corrosive protection, it is recommended to apply an additional layer, as described above.

## Special notes

- **Neotex® Metal Primer** should not be applied under wet conditions, or if wet conditions or rainy weather are expected to prevail during the application or the curing period of the product.
- The substrate temperature must be at least 3°C above dew point to reduce the risk of condensation or blooming on the surface finish
- In case that an extended period of time (>2 days) has passed between successive layers, it is recommended to lightly sand the surface of the previous layer, in order to avoid possible adhesion problems of the next layer
- Not recommended for application on substrates of stainless steel. In that case, the application of **Neotex® Inox Primer** is recommended instead.

<b>Colour</b>	Terracotta
<b>Packing</b>	3L and 1L in plastic pails
<b>Cleaning of tools – Stains removal</b>	By water immediately after the application. In case of hardened stains, by mechanical means only.
<b>Volatile organic compounds (V.O.C.)</b>	V.O.C. limit acc. to the E.U. Directive 2004/42/CE for this product of category AiWB: 140g/l (Limit 1.1.2010) - V.O.C. content of the ready-to-use product <140g/l
<b>UFI code</b>	QNA0-00UM-V00H-VE13
<b>Storage stability</b>	2 years, stored in the original sealed packing, protected from frost, humidity and exposure to solar radiation.



The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX® SA. It is offered as a service to designers and contractors to help them find potential solutions. However, as a supplier, NEOTEX® SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.

**HEADQUARTERS - PLANT**  
V. Moira str., Xiropigado  
**LOGISTICS SALES & CENTER**  
Loutsas str., Voro

P.O. Box 2315, GR 19600  
Industrial Area Mandra  
Athens, Greece  
T. +30 210 5557579

**NORTHERN GREECE BRANCH**  
Ionias str., GR 57009  
Kalochori, Thessaloniki, Greece  
T. +30 2310 467275

[www.neotex.gr](http://www.neotex.gr) ● [export@neotex.gr](mailto:export@neotex.gr)