

## Neotex<sup>®</sup> Inox Primer

**Water-based primer for inox, aluminium, galvanized surfaces**

### Description

Water-based, one-component primer, ideal for applications on inox and galvanized surfaces, aluminium, tinplate, glass

### Fields of application

On substrates of stainless or galvanized steel, aluminium, tinplate, glass, etc. prior to the application of brushable waterproofing or protection coatings

### Properties - Advantages

- May be overcoated with water-based, solvent-based or solvent-free products, without the need for any special surface treatment prior to overcoating
- One-component and easy to apply
- Excellent adhesion on most glossy non-porous surfaces
- Does not contain toxic substances or solvents
- Fast-drying



### Appearance - Colour

Semi-transparent - Blue

### Packing

3L and 1L

### Technical characteristics

Density (EN ISO 2811-1)	1,04kg/L (±0,05)
-------------------------	------------------

**Consumption: 60-75ml/m<sup>2</sup> in one layer**

### Application conditions

Substrate moisture content	<4%
Relative air humidity (RH)	<65%
Application temperature (ambient - substrate)	+10°C min. / +35°C max.



### Curing details

Drying time (+25°C, RH 50%)	1 hour
Dry to overcoat (+25°C, RH 50%)	10 hours
<i>* Low temperatures and high humidity during application and/or curing prolong the above times, while high temperatures reduce them</i>	

### Instructions for use

#### **Substrate preparation**

The surface must be clean, dry and free of dust, oil, grease, older coatings and loose materials. In case it is not possible to thoroughly clean the surface from loose materials or existing poorly adhering coatings, it is recommended to sand with fine sandpaper and then clean the surface with solvent **Neotex® 1021**.

#### **Application**

**Neotex® Inox Primer** is applied, undiluted, by suitable enamel paint roller, paint brush or airless spray, in one thin layer.

### Special notes

- **Neotex® Inox Primer** should not be applied under wet conditions, or if wet conditions or rainy weather are expected to prevail during the application or the curing period of the product.
- **Neotex® Inox Primer** should be only applied in a single layer of thin thickness

<b>Appearance</b>	Thin liquid
<b>Appearance (cured) - Colour</b>	Semi-transparent - Blue
<b>Packing</b>	3L and 1L in plastic pails
<b>Cleaning of tools – Stains removal</b>	By water immediately after the application. In case of hardened stains, by mechanical means only.
<b>Volatile organic compounds (V.O.C.)</b>	V.O.C. limit acc. to the E.U. Directive 2004/42/CE for this product of category AiWB: 140g/l (Limit 1.1.2010) - V.O.C. content of the ready-to-use product <140g/l
<b>UFI code</b>	1KA0-H057-K001-62F1
<b>Storage stability</b>	2 years, if kept in the original sealed packaging, protected from frost, humidity and exposure to solar radiation.



The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX® SA. It is offered as a service to designers and contractors to help them find potential solutions. However, as a supplier, NEOTEX® SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.

**HEADQUARTERS - PLANT**  
V. Moira str., Xiropigado  
**LOGISTICS SALES & CENTER**  
Loutsas str., Voro

P.O. Box 2315, GR 19600  
Industrial Area Mandra  
Athens, Greece  
T. +30 210 5557579

**NORTHERN GREECE BRANCH**  
Ionias str., GR 57009  
Kalochori, Thessaloniki, Greece  
T. +30 2310 467275

[www.neotex.gr](http://www.neotex.gr) ● [export@neotex.gr](mailto:export@neotex.gr)